

A·R·C·HITECTURAL[®]

ROOF COATINGS



MADE IN  THE USA

● **PRODUCT DATA SHEET**

HydroSHIELD™ T R. I. P. 2 S

DESCRIPTION

HydroSHIELD™ T2S RIP is a water based rust inhibitive primer. This acrylic primer dries by dehydration. HydroSHIELD™ T2S RIP adheres to metallic and corroded carbon steel. Use over lightly rusted steel. Is U.V. stable.

RECOMMENDED USES

HydroSHIELD™ T2S RIP to be applied to corroded metal surfaces. Allow to cure 24 hours before application of the ARC coating.

APPLICATION

Apply when ambient temperature is 50° F and rising. Surface to be treated must be clean. If necessary, remove all dust, grease and loose debris before applying this product. Apply HydroSHIELD™ T2S RIP by roller, brush or spray at a rate of 0.5 to 1.5 gallons per 100 square feet. Multiple passes may be applied waiting 2 hours between applications when applied at ambient temperature of 70° F and rising.

BENEFITS

- Anti Corrosion Protection
- Stops Rust
- Excellent Primer
- Non-Toxic
- Easy Clean Up
- Prevents Rust
- Nano-processed

Avoid breathing fumes and prolonged contact with skin. Do not ingest. Keep containers covered when not in use. When using, provide proper ventilation. Dispose of product and container in accordance with local disposal codes.

TECHNICAL DATA

COLOR:	Yellow
VISCOSITY:	5000 - 6000 cps +/- 5%
FUNGAL RESISTANCE:	Passed ASTM D-3273-73T
CLEAN UP:	Soap and water
APPLICATION RATE:	0.5 to 1.5 gallons per 100 Sq.Ft.
DRY TIME: (dehydration)	2-4 hours @ 70° F
SOLIDS BY WEIGHT:	55% +/- 5% ASTM D- 1644
SOLIDS BY VOLUME:	48% +/- 5% ASTM D- 2697
VOC:	<50 grams per liter
WEIGHT:	10.9 lbs. per gallon +/- 5%

PRECAUTION: If rain or fog is expected within 24 hours, DO NOT APPLY. This product sets by dehydration. Do NOT leave in spray hose overnight. FLUSH SPRAY LINES.

Not recommended to use HydroSHIELD™ T2S Activator to set HydroSHIELD™ T2S R.I.P.

System warranty available. When sold separate from system there is no warranty given, expressed or implied, through the values or statements made here, nor are there any assertions that the product purchased has been individually tested to conform to these standards. Testing is performed on a random basis by our in house and independent third party labs in order to obtain approval and/or classification. Acceptance, purchase and selection of these products are the sole responsibility of the buyer, buyer's agent, or the buyer's customer. ARC assumes no responsibility for coverage, performance, or injuries resulting from use. Liability, if any, is limited to replacement of the product. NO OTHER GUARANTY OR WARRANTY OF ANY KIND IS MADE BY ACE ROOF COATINGS, INC. OR ITS SUBSIDIARIES, EXPRESSED OR IMPLIED, STATUTORY, BY OPERATION OF LAW, OR OTHERWISE, INCLUDING COSMETIC APPEARANCE, MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE.

ARCHITECTURAL ROOF COATINGS, INC.®

Product Data Sheet

APPLICATION PROCEDURES

FOR ALL HYDROSHIELD™ and HYDRO-THERM™ ROOF COATINGS

TEMPERATURE

Air and Surface: 45°F Minimum/140°F Maximum

Material: 45°F Minimum/100°F Maximum

RELATIVE HUMIDITY

Can be applied at relative humidity up to 95%

DO NOT APPLY WHEN THE TEMPERATURE CAN FALL TO WITHIN 5°F OF THE DEW POINT WITHIN 6 HOURS.

This product cures by water evaporation. It is very important that this product is not used when weather conditions are below 45°F or when there is a chance that the temperature could fall below 20°F within a 24 - hour period after application. Do not apply this product if rain or dew is likely to occur before drying of product. Late afternoon application is not recommended if high humidity conditions exist, which could cause high moisture concentration on the surface overnight.

BRUSH: No reduction necessary. Use nylon/polyester brush. Do not over-brush as material may start to pull.

ROLLER: No reduction necessary. Use 1/2" to 1-1/2" nap synthetic rollers. Keep a wet edge to avoid ripping which may change appearance. If ripping is a problem, extend lap time to after materials have skinned. Avoid rapid rolling which causes bubbling.

AIRLESS SPRAY-VOLUME:

Output: 2.0 – 3 gal. per min.

Pressure: 3,000 – 4,000 psi

Spray Gun: Graco – Contractor rated for pressure

Fan/Tip: 12/.021 -12/.039 reversible

Extension: 12" – 36" gun extension recommended

SPECIAL CONDITIONS

Mildew:

- Must be removed by power washing and broom scrubbing with a solution of bleach or liquid detergent and water. Rinse clean and allow dry.

Ponding Water:

- **ARC's Warranties do not cover damage to ARC coating caused from areas that pond water.**
- Water based coatings should not be applied on roofs that collect water and results in standing water over 48 hours after a rain. The National Roofing Contractors Association considers water ponds on any roof unacceptable. (See the NRCA Roofing and Waterproofing Manual).
- Do not use without a vapor barrier on cold storage or cryogenic tank roofing applications.

Surface Preparation: All surfaces to be coated must be clean, dry, and paintable. It may be necessary to power wash and/or prime to enhance adhesion. See application specification for more details.

Mixing Procedures: No thinning or reducing is necessary. Product may separate after shipping and storage, though it may still look mixed. When mixing becomes necessary, we recommend the use of a 3/4 horsepower or larger electric or air operated mixer with a blade capable of uniformly mixing the entire container. When product is in 5-gallon pails, use a 3" minimum diameter mixing blade. When product is in drums, use a 6" minimum diameter mixing blade.

Application Equipment: This product may be sprayed, brushed, or rolled. When using spray equipment, it is important that the following criteria are met: When using a spray pump, a 30:1 or 40:1 greater fluid to air ratio capable of delivering 2 gallons or more per minute continuous is needed, as well as an aluminum window screen. If a fluid spray hose is used, it should be high pressure with designed working pressure to handle maximum pressure delivered by the spray pump. Inside lining or tube should be of such a material so it is unaffected by the coating and any solvents used in clean up. Additionally, the following criteria should be used for hoses: 3/8" minimum I.D. up to 75 feet; 1/2" minimum I.D. up to 200 feet; and 3/4" minimum I.D. over 200 feet. The larger I.D. sections of hose should be used from the pump out in all circumstances with additional hose size reductions as necessary.

If a gun hose whip is used, high pressure with adequate W.P.S.I. 3/8" I.D. X 6 feet with an appropriate lining or tube is recommended. When using a spray gun, we recommend the Graco Hydra Max or equivalent. High-pressure gun swivels are available and can reduce operator fatigue. Spray tip should be a reversible self-cleaning type with an orifice size of .021 to .039 with a fan angle of 35 to 55 degrees. Always use components rated for pump pressures.

Cleanup Instructions: Clean up spills and spatters immediately with water. After cleaning, flush entire spray equipment with water followed by flushing propylene glycol through metal pump parts to prevent unit from rusting.

SAFETY PRECAUTIONS: Refer to the MSDS sheet before use. For Chemical emergencies, spills, leaks, exposure, or accidents CALL: INFOTRAC DAY/NIGHT 1-800-535-5053

System warranties available. When sold separately from system there is no warranty given, expressed or implied, through the values or statements made here, nor are there any assertions that the product purchased has been individually tested to conform to these standards. Testing is performed on a random basis by our in-house and independent third-party labs in order to obtain approval and/ or classification. Acceptance, purchase, and selection of these products are the sole responsibility of the buyer or buyer's representative. ARC assumes no responsibility for coverage, performance or injuries resulting from use. Liability, if any, is limited to replacement of the product. NO OTHER WARRANTY OR GUARANTEE OF ANY KIND IS MADE BY ARCHITECTURAL ROOF COATINGS, INC. EXPRESSED OR IMPLIED; STATUTORY, BY OPERATION OF LAW, OR OTHERWISE, INCLUDING MERCHANTABILITY, COSMETIC APPEARANCE, AND FITNESS FOR A PARTICULAR PURPOSE.